

TECHNICAL DATA SHEET

2 02.09.2014

**GORI 640-01
KNOT SEALER**

Primer for flow coating / dipping

Page 1 of 2

GORI 640 KNOT SEALER, a water borne industrial primer for new wood designated for exterior use such as windows and doors.

GORI 640 KNOT SEALER minimizes yellowing of knots and wood with a large amount of heartwood.

TECHNICAL DATA

| | |
|----------------------------------|---|
| Binder: | Synthetic binder |
| Solid content: | Approx. 50 % w/w |
| Viscosity: | Approx. 13 s in DIN cup 4 mm at 20 °C |
| Volatile organic compound (VOC): | See Safety Data Sheet. |
| Theoretical consumption: | 6-8 m ² /l May vary according to wood quality and application method. |
| Colour range: | White and antique white |

APPLICATION DETAILS

| | |
|-------------------------|---|
| Pre-treatment: | The wood must be clean and free from wood dust and contamination. The moisture content of the wood should be approx. 13 % and should not exceed 15 %. All softwood for exterior use should either be vacuum impregnated or treated with a wood preservative. |
| Application: | To be applied by flow coating or dipping. Due to evaporation, the solid content of the liquid must be adjusted with water regularly. |
| Application conditions: | The product is delivered ready for use. Stir the product well before use. Film thickness – achieved by 2 x flow coat: 125-175 µm wet Optimum temperature for products and surroundings: 18-22 °C Optimum relative air humidity: Approx. 50 % |
| System treatment: | Primed parts must always be protected with a topcoat treatment before they are exposed to the influence of the weather. |

TECHNICAL DATA SHEET

2 02.09.2014

Page 2 of 2

GORI 640-01 KNOT SEALER

Drying times: Determined at 20 °C and 50 % relative humidity:

Dry to handle: 1-2 hours
Dry to sand* / dry to recoat: 2-3 hours

*As the layer thickness is of paramount importance for the effectiveness of the product, it is important not to sand the surface too much.

The drying time can be reduced using special drying systems to force drying. The drying times are approximate and may vary according to wood quality, temperatures, humidity, ventilation and film thickness.

Cleaning: The equipment is cleaned with water.

HEALTH AND SAFETY See Safety Data Sheet.

ADDITIONAL INFORMATION

Pack size: 3, 10, 20, 120, 600 and 1,000 l

Storage: The product must be stored at temperatures above 5 °C. Shelf life in unopened containers: See "Best before date" on the label. Keep containers tightly closed after use.

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.