

TECHNICAL DATA SHEET

2 02.09.2014

**GORI 649-XX
BALCONY PRIMER**

Primer for flow coating / dipping

Page 1 of 2

GORI 649 Balcony Primer is a water borne industrial primer for the treatment of wooden balcony parts.

GORI 649 Balcony Primer minimizes patchiness in subsequent translucent surface treatments.

TECHNICAL DATA

Binder:	Synthetic binder	
Solid content:	Translucent:	Approx. 10 % w/w
	White/opaque:	Approx. 50 % w/w
Viscosity:	Translucent:	Approx. 50 s in DIN cup 2 mm at 20 °C
	White/opaque:	Approx. 14-16 s in DIN cup 4 mm at 20°C
Volatile organic compound (VOC):	See Safety Data Sheet.	
Theoretical consumption:	Translucent:	Approx. 25 m ² /l
	White/opaque:	Approx. 6-8 m ² /l
	May vary according to wood quality and application method.	
Colour range:	Variant 11:	Base T (translucent colours)
	Variant 21:	Base 1 and 3 (white and opaque colours)

ANVENDELSESTEKNISKE DATA

Pre-treatment:	The wood must be clean and free from wood dust and contamination. The moisture content of the wood should be approx. 13 % and should not exceed 15 %.	
	All softwood and non-durable hardwood for exterior use should either be vacuum impregnated (only softwood) or treated with a wood preservative.	
Application:	To be applied by flow coating or dipping. Due to evaporation, the solid content of the liquid must be adjusted with water regularly.	
Application conditions:	The product is delivered ready for use. Stir the product well before use.	
	Film thickness:	40 µm wet
	Optimum temperature for products and surroundings:	18-22 °C
	Optimum relative air humidity:	Approx. 50 %
System treatment:	Primed parts must always be protected with a topcoat treatment before they are exposed to the influence of the weather.	
	For translucent colours use:	GORI 661-11 Balcony Topcoat
	For white and opaque colours use:	GORI 661-01

TECHNICAL DATA SHEET

2 02.09.2014

**GORI 649-XX
BALCONY PRIMER**

Page 2 of 2

Drying times: Determined at 20 °C and 50 % relative humidity:

Dry to handle: 1-2 hours

Recoating time: 3-4 hours

The drying time can be reduced using special drying systems to force drying. The drying times are approximate and may vary according to wood quality, temperatures, humidity, ventilation and film thickness.

Cleaning: The equipment is cleaned with water.

HEALTH AND SAFETY See Safety Data Sheet.

ADDITIONAL INFORMATION

Pack size: 20 and 120 l

Storage: The product must be stored at temperatures above 5 °C. Shelf life in unopened containers: See "Best before date" on the label. Keep containers tightly closed after use.

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.